

Composition

54% Japanese Paper, 46% Viscose

キャラクター

軽さとコシの強さを特徴とする和紙糸と、柔らかく光沢のあるビスコースを撚り合わせました。和紙とビスコースで光沢感が異なるため色に奥行きが生まれ、涼しげな見た目が特徴です。和紙糸ならではのさらっとした清涼感のある風合いに、レーヨンの落ち感をプラスすることで上品さをもたらしました。

特記事項

製造工程の特性上、若干の斜行が起こる場合があります。予めご了承ください。
1コーンあたりの重量は0.8kgです。

ご使用時の注意点

- 品質の保持には十分努力しておりますが、生産ロット間の差異にはご注意をお願い致します。
- 編み組織や本数取り、色でも縮率は異なりますので、必ずテストをしてからのご使用をお願い致します。

ストックサービス

一部ストックあり

ブックカラーミニマム

営業担当者にお問い合わせください。

別注色

○

別注色ミニマム

営業担当者にお問い合わせください。

適正ゲージ (参考)

7GG 2ply

洗濯絵表示例



12GG 1ply

※洗濯表示につきましては、編み組織、デザイン、付属等を含めてご検討下さい。

Characteristics

Summery yarn characterized by dry touch, lightweight, and strong texture.
Made from Japanese paper and viscose, two different materials create a beautiful contrast of color and brightness.

Special Instructions

Due to its production method, the yarn tends to twist in certain stitches.
This article is around 0.8 kg per cone.

Notes

- Please note that the small differences of colour/texture/shrinkage between the production lots are inevitable.
- Please conduct enough trials in advance, as the final result depends greatly on the condition of knitting and washing.

Stock Service

All colors are available for sampling.

Minimum Order Quantity

0.8 kg per colour

Your Own Colour

Yes

MOQ for your own colour

6 kg per colour

Dyeing Bath Lot

Top Dye (Melange)

Min: N/A

Yarn Dye (Solid)

Min: 6 kg

Max: N/A

Max: 100 kg (1 Lot)

Finishing

This is the instruction for finishing the product. For the care instructions, please refer to the labeling below.

- Washing at low-temperature water is recommended. Please steam press to set the shape before washing. After washing, please dry at low temperature.
- When ironing, please put a piece of cloth on the knitted panel. The temperature must be below 110°C.

Colour Fastness

Water at 37°C

Grade 3/4

Light fastness

Grade 4

Dry rubbing

Grade 3/4

Wet rubbing

Grade 3/4

Pilling Test

Grade 3/4

Suitable Gauge

7GG 2ply

Labeling

12GG 1ply

